

Carpenter Goodwin 31 Bridge St Leominster Herefordshire HR6 8DU 01568 616266 www.carpentergoodwin.co.uk

600108KR RAL6001 Emerald Green Mchale Green equiv. Machinery paint 1 Litre



RAL 6001

*Colour swatch for guidance only 600108KR Part No: 600108KR Price: £14.80 (exc VAT) | £17.76 (inc VAT)

Specifications

Kramp 600108KR 1 Litre RAL6001 Emerald Green paint - Mchale Green equivalent Machinery paint shade also simiar to Castrol Green paint shade.

Suitable for some Spearhead Hedgecutter, Mchale Machinery and Hagedorn Green Machinery paint applications.

Specifications	 High UV and weather resistance Very easy to work with, high final hardness, lasting gloss Chromate-free and lead-free
Benefits	- Long service life - Efficient working - Low environmental impact
Application	 Surface treatment for use in the industrial sector, for tractors, agricultural machines and civil engineering machinery For iron and steel Resistant to benzine and diesel oil for short-term contact

Properties	 Bonding agent base: modified alkyd resins Dry solids: 52-58% Basic viscosity (DIN 53 211): thixotropic Specific weight (DIN 51 757): 0.97-1.18 kg/l Gloss level (DIN 67 530) >80%/60° (high gloss) Temperature resistance: continuous load 130°C, short-term load 150°C Application conditions: from +10°C and up to 80% relative humidity Set to touch after 6-8 hours (at 20°C) Hardened after 24 hours (at 20°C) Final hardness after 3-4 days (at 20°C) Base coat: Kramp primer (coat thickness: 50-60 µm) Top coat: Kramp synthetic resin varnish (coat thickness: 50-60 µm) Theoretical coverage per litre: 3.8-4.2 m²/kg (with a coat thickness of 50 µm)
Technical information	 Surface preparation: The object to be treated must be thoroughly cleaned, degreased and sanded as necessary Some types available in semi-gloss finish and matt Complies with Austrian Solvents Ordinance (dated 1/1/96) Drying times can be shortened by using Kramp quick-drying thinners instead of Kramp synthetic resin thinners Lower temperatures result in longer drying times
Unit	Each
Dust dry at (20 °C) (min)	30-60
Colour	Emerald green
Туре	Synthetic resin
Capacity (I.)	1